

## PolyCore™ ABS-5012

Technical Data Sheet (Ver. 1.0, last updated: June, 2020)

PolyCore™ ABS-5012 is 20% Glass fiber reinforced ABS pellets featured with great cost effectiveness and excellent printability, designed for Big Area Additive manufacturing (BAAM) technology.

### Physical Properties<sup>1</sup>

Property	Testing Method	Typical Value
Density (g/cm <sup>3</sup> at 21.5 °C)	ASTM D792 (ISO 1183, GB/T 1033)	1.21
Melt index (g/10 min)	220 °C, 10 kg	12.7
Glass transition temperature (°C)	DSC, 10 °C/min	96
Vicat Softening temperature (°C)	ASTM D1525 (ISO 306 GB/T 1633)	109
Heat Deflection Temperature (°C)	ISO 75 1.8MPa	96
	0.45MPa	102

1. Tested with injection molding specimens

### Mechanical Properties<sup>1</sup>

Property	Testing Method	Typical Value
Young's modulus (MPa)	ASTM D638 (ISO 527, GB/T 1040)	7343 ± 158
Tensile strength (MPa)	ASTM D638 (ISO527, GB/T 1040)	90.6 ± 0.9
Elongation at break (%)	ASTM D638 (ISO527, GB/T 1040)	2.3 ± 0.1
Bending modulus (MPa)	ASTM D790 (ISO 178, GB/T 9341)	6328 ± 317
Bending strength (MPa)	ASTM D790 (ISO 178, GB/T 9341)	119.3 ± 2.7
Charpy Impact strength (kJ/m <sup>2</sup> )	ASTM D256 (ISO 179, GB/T 1043)	9.2 ± 0.2

1. Tested with injection molding specimens

## Recommended Printing Conditions

Parameter	Recommended Setting
Air drying temperature (°C)	80
Air drying time (h)	3 - 4
Maximum moisture content (%)	0.02
Barrel – zone 1 temperature (°C)	210 - 220
Barrel – zone 2 temperature (°C)	220 - 240
Barrel – zone 3 temperature (°C)	230 - 250
Nozzle temperature (°C)	230 - 240
Bed temperature (°C)	40 - 80
Other Comments	
<ul style="list-style-type: none"> <li>● It is recommended to stop feeding and continue extruding until the extruder is fully empty, if the printing stops in a short term, such as 10-30 min</li> <li>● It is recommended to stop feeding and continue extruding until the extruder is fully empty, then use polyethylene (PE) to clean the extruder, if the printing stop in a long term, such as several hours. It is helpful to avoid the carbonization of material and keep extruder working in a good condition</li> </ul>	

## Disclaimer

The typical values presented in this data sheet are intended for reference and comparison purposes only. They should not be used for design specifications or quality control purposes. Actual values may vary significantly with printing conditions. End-use performance of printed parts depends not only on materials, but also on part design, environmental conditions, printing conditions, etc. Product specifications are subject to change without notice.

Each user is responsible for determining the safety, lawfulness, technical suitability, and disposal/recycling practices of Polymaker materials for the intended application. Polymaker makes no warranty of any kind, unless announced separately, to the fitness for any particular use or application. Polymaker shall not be made liable for any damage, injury or loss induced from the use of Polymaker materials in any particular application.