


TECHNICAL DATA SHEET



V2.0



PolyWood™


PolyWood™ is a wood mimic filament without actual wood powder, which removes all risks of nozzle clogs. PolyWood™ is made entirely with PLA using a special foaming technology. It exhibits the same density and appearance as wood.

WWW.POLYMAKER.COM

PHYSICAL PROPERTIES

PROPERTY	TESTING METHOD	TYPICAL VALUE
Density	ISO1183, GB/T1033	0.9 g/cm ³ at 23°C
Melt index	N/A	N/A
Light transmission	N/A	N/A
Flame retardancy	N/A	N/A


MOISTURE ABSORPTION CURVE



THERMAL PROPERTIES

PROPERTY	TESTING METHOD	TYPICAL VALUE
Glass transition temp.	DSC, 10°C/min	59 °C
Melting temp.	DSC, 10°C/min	151 °C
Crystallization temp.	DSC, 10°C/min	N/A
Decomposition temp.	TGA, 20°C/min	N/A
Vicat softening temp.	ISO 306, GB/T 1633	60 °C
Heat deflection temp. (1.8MPa)	ISO 75 1.8MPa	50 °C
Heat deflection temp. (0.45MPa)	ISO 75 0.45MPa	54 °C

HDT CURVE



MECHANICAL PROPERTIES

PROPERTY	TESTING METHOD	TYPICAL VALUE
Young's modulus (X-Y)	ISO 527, GB/T 1040	1688.5 ± 80.8 MPa
Young's modulus (Z)		1726.3 ± 199.8 MPa
Tensile strength (X-Y)	ISO 527, GB/T 1040	24.4 ± 0.3 MPa
Tensile strength (Z)		20.8 ± 0.9 MPa
Elongation at break (X-Y)	ISO 527, GB/T 1040	8.8 ± 0.3 %
Elongation at break (Z)		2.0 ± 0.4 %
Bending modulus (X-Y)	ISO 178, GB/T 9341	1958.9 ± 72.6 MPa
Bending modulus (Z)		N/A
Bending strength (X-Y)	ISO 178, GB/T 9341	50.2 ± 1.6 MPa
Bending strength (Z)		N/A
Charpy impact strength (X-Y) notched	ISO 179, GB/T 1043	2.4 ± 0.3 kJ/m ²
Charpy impact strength (Z) notched		N/A

CHEMICAL RESISTANCE DATA

PROPERTY	TYPICAL VALUE
Effect of weak acids	Good
Effect of strong acids	Poor
Effect of weak alkalis	Fair
Effect of strong alkalis	Poor
Effect of oils and grease	Good

Good:
Material may get minor attack after long periods of storage with chemical at ambient temperature

Fair:
Material can be used for short time contact with chemicals at ambient temperature

Poor:
Material becomes unstable on contact with chemical at ambient temperature

RECOMMENDED PRINTING CONDITIONS

Nozzle temperature	190 – 210 (°C)
Build plate temperature	25 - 60 (°C)
Build surface treatment	PC and Texture PEI (Glue when needed)
Cooling fan	ON
Closure chamber	No Needed
Recommended support material	PolySupport™ and PolyDissolve™ S1

Printing speed	50 - 100 (mm/s)
Drying temp. and time	55°C for 6h
Retraction distance	3 - 6 (mm)
Retraction speed	40 - 60 (mm/s)
Annealing setting	-

*Based on 0.4mm nozzle. Printing conditions may vary with different nozzle diameters.




PolyBox™ or PolyDryer™ Box
Recommended storage for excellent printing quality

HOW TO MAKE SPECIMENS


Printing temperature	210 °C
Bed temperature	50 °C
Top & bottom layer	3
Environmental temperature	Ambient

Infill	100%
Shell	2
Cooling fan	ON


FLEXURAL TESTING SPECIMEN ISO 178, GB/T 9341



TENSILE TESTING SPECIMEN ISO 527, GB/T 1040



IMPACT TESTING SPECIMEN ISO 179, GB/T 1043



DISCLAIMER

The typical values presented in this data sheet are intended for reference and comparison purposes only. They should not be used for design specifications or quality control purposes. Actual values may vary significantly with printing conditions. End-use performance of printed parts depends not only on materials, but also on part design, environmental conditions, printing conditions, etc. Product specifications are subject to change without notice.

Each user is responsible for determining the safety, lawfulness, technical suitability, and disposal/recycling practices of Polymaker™ materials for the intended application. Polymaker™ makes no warranty of any kind, unless announced separately, to the fitness for any use or application. Polymaker™ shall not be made liable for any damage, injury or loss induced from the use of Polymaker™ materials in any application.